

## GEOTEXTILES

### Product Data Sheet

Issue: 01.TGT21 Date: 01.13 Page: 1 of 1

AASHTO Class M288			-	-	-	-	3	2	2	1	1
			TYPAR 3151	TYPAR 3201	TYPAR 3301	TYPAR 3341	TYPAR 3401	TYPAR 3501	TYPAR 3601	TYPAR 3801	TYPAR 3100
<b>Mechanical (Marv)<sup>1</sup></b>											
Grab tensile strength	ASTM D4632	lbs	35	60	120	120	130	160	240	300	335
Grab elongation	ASTM D4632	%	60	60	60	60	60	60	60	60	61
Trapezoidal tear strength	ASTM D4533	lbs	15	25	35	40	60	60	90	95	74
Puncture strength	ASTM D4833	lbs	10	18	25	34	41	56	67	93	-
CBR Puncture	ASTM D6241	lbs	-	-	-	-	225	310	370	510	697
<b>Endurance (MARV)<sup>1</sup></b>											
UV Resistance @ 500 hrs	ASTM D4355	%	-	-	-	70	70	70	70	70	-
<b>Hydraulic (MARV)<sup>1</sup></b>											
Apparent opening size <sup>2</sup>	ASTM D4751	US Sieve	20/30	30	50	60	70	70	140	170	-
Permittivity	ASTM D4491	sec <sup>-1</sup>	1.5	1.0	0.8	0.7	0.7	0.5	0.1	0.1	0.123
Water flow rate	ASTM D4491	gal/min/ft <sup>2</sup>	235	190	95	85	60	50	15	8	-
<b>Physical (Typical)</b>											
Unit weight		oz/yd <sup>2</sup>	1.6	1.9	3.0	3.4	4.0	5.0	6.0	8.0	10
Roll diameter		in	7	7	8	8	9	10	10	12	-
Length		yd	100	100	100	100	100	100	100	100	-
Width		in	151	151	151	151	151	151	151	151	-
Roll area		yd <sup>2</sup>	419	419	419	419	419	419	419	419	-
Roll weight gross		lbs	50	58	87	97	113	138	165	218	-
Width		in	-	-	-	-	187	187	187	187	-
Roll area		yd <sup>2</sup>	-	-	-	-	519	519	519	519	-
Roll weight gross		lbs	-	-	-	-	142	175	209	275	-

20% Recycled Content

As part of its continual improvement process, Fiberweb, Inc. reserves the right to change the properties listed on this data sheet without prior notice.

® indicates a registered trademark of Fiberweb, Inc. or a Fiberweb Group company, many of which are registered in a number of countries around the world.